Technical Information Sheet

CERAMIC COATED ROOFING GRANULES

Item Description	Item Number
White	W70RACGGWH
Black	W70RACGGBK

DESCRIPTION

Ceramic coated roofing granules are made available in 50 lb (22.7 kg) metal pails.

METHOD OF APPLICATION

Elevate recommends that granules be applied to areas of asphalt "bleed-out" while the asphalt is still in a molten state, as well as bleed out from cold adhesive or when liquid flashing is applied. Areas of "bleed-out" at inside and outside corners require application of granules.

PRECAUTIONS

- Refer to Safety Data Sheets (SDS) for additional safety information.
- Minimize the amount of dust generated when applying or handling this product. Use in well ventilated area.

ENVIRONMENTAL METRICS

Recycled Content	
Post-Consumer	0%
Post-Industrial	0%

PRODUCT PACKAGING

Properties	Value
Pail	5 Gallon (18.9 L)
Weight	50 lb (22.7 kg)
Pallet Size	48" x 39" (1.2 m x 1.0 m)
Pails per Pallet	36
Pallet Weight	1800 lb (816.5 kg)
Pallets per Truckload	24

PHYSICAL PROPERTIES

Properties	Value
Dust	0.2% Maximum <100 Mesh US Sieve (150 µm)
Moisture Content	0.3% Maximum
Hardness	6.0 – 7.0 Moh's Mineral Scale
Specific Gravity	2.6 – 2.9

Please contact Elevate Technical Services at 800-428-4511 for further information.

This sheet is meant to highlight Elevate products and specifications and is subject to change without notice. Amrize takes responsibility for furnishing quality materials that meet published Elevate product specifications or other technical documents, subject to normal manufacturing tolerances. Neither Amrize nor its representatives practice architecture. Amrize offers no opinion on and expressly refuses any responsibility for the soundness of any structure. Amrize accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No Amrize representative is authorized to vary this disclaimer.